

Technical Data Sheet

Description

P9.3.K1 is a 2K, VOC compliant, high build, anti sag epoxy primer with built in corrosion resistance and excellent adhesion onto properly prepared hot or cold roll steel, aluminum and many other non-ferrous metals, fiberglass and over properly prepared 2K painted surfaces.

Suggested Use

As a wet on wet sealer or a full bodied sand-able primer.

Over any of the above mentioned properly prepared substrates where:

- High level of corrosion resistance is needed.
- Excellent adhesion is needed.
- High productivity is required.
- VOC restrictions are present.
- Excellent performance when applied with airless, air-assist airless pressure pot, cup gun or brush or rolled.

Components

P9.3.K1

GSR-F, GSR-M, GSR-S

GSOR-F, GSOR-M, GSOR-S

EH.001

Base

Fast, Medium, Slow Reducer for National Rule Applications

Fast, Medium, Slow Zero VOC Reducer for Compliant Applications

Hardener

Field Applications

- Semi-trucks
- Structural steel
- Coachworks (Buses)
- Work panel trucks
- Trailers and frames
- Construction equipment

GlobalStar

P9.3.K1

HS Gray Epoxy Primer

GlobalStar
INDUSTRIAL



US/08232016P9.3.K1

- Cement trucks and snow plows
- Many OEM applications
- Oil Field Equipment
- Aircraft and marine

Mixing Ratio

Mix:

One (1) part P9.3.K1 Epoxy Base to one (1) part EH.001 Epoxy Hardener. Reduce 0%-25% with selected reducer.

Application

Apply:

one to two medium wet coats, allow 10-20 minutes flash between coats.

Or Apply one medium light coat followed by a medium cross coat.

Spray Gun:

HVLP Gravity Feed – 1.4 – 1.7mm tip and needle
Pressure Pot HVLP – 1.0 – 1.2mm tip and needle
Air Assist Airless – 1.0 – 1.2mm tip and needle
Conventional – 1.5 – 1.8mm tip and needle
Airless – 310 – 610 – 313 – 613 nozzle

Film Build:

50-100 microns – (2.0 – 4.0 mils.)

Dry Times

Dust Free:

20-30 minutes @ 20° C (68° F)

Dry to Touch

3-4 hours @ 20° C (68° F)

Total Hardness

48 hours @ 20° C (68° F)

Force Dry

30 minutes @ 60° C (140° F)

Surface Preparation

Ferrous metals:

Best Case

SA2 sandblast Blow all dust and contaminants off and apply P9.3.K1 primer within 8 hours.

Second Best Case

Hot Phosphate wash system, blow dry and apply P9.3.K1 primer

GlobalStar Industrial

GlobalStar

P9.3.K1

HS Gray Epoxy Primer

US/08232016P9.3.K1

Within 8 hours.

Third Best Case

Careful mechanical abrasion. Clean all dust, oil residue, finger prints and contaminants before and after mechanical abrasion with a clean drying wax and grease removal solvent making sure all residue is removed then apply P9.3.K1 primer within 4 hours.

Aluminum:

Clean surface with clean drying wax and grease remover, apply P9.3.K1 Epoxy Primer within 4 hours.

Galvanized Steel:

Clean all dust, oil residue, and contaminants from surface using a Clean drying wax and grease remover. Light Sanding (320P grit) Clean again with clean drying wax and grease remover using a wipe and dry process, apply P9.3.K1 epoxy primer as directed.

VOC

Regulatory VOC

252 g/l (2.1 lbs./gl.)

Actual VOC

204 g/l (1.7 lbs./gl.)

Solids

By Volume

39%

By Weight

55%

Specific Gravity

0.984 kg/l (9.2 lbs./gl.)

Coverage

313.0 square feet per gallon @ 100% transfer efficiency

@ 50 microns (2 mils.)

58.1 square meters per gallon @ 100% transfer efficiency

@ 50 microns (2 mils)

GlobalStar Industrial

GlobalStar

P9.3.K1

HS Gray Epoxy Primer

US/08232016P9.3.K1

Repainting

After 48 hours @ 20° C (68° F) light sanding needed.

Adhesion

(ASTM D 4541)
(ASTM D 3359)

1850 psi - Excellent
A/B (5/5) – Excellent

Salt Spray

(ASTM B 117)

Pass 1500 hours

Direct Impact

(ASTM D 2794)

Very Good (140 in-lb.)

Reverse Impact

(ASTM D 2794)

Very Good (50 in-lb.)

Humidity Resistance

(ASTM D 2247)

Pass 1000 hours

Flexibility

(ASTM D 522)

Excellent (Mandrel)

Storage Stability

One year, stored in closed package, in cool dry place, away
From any sources of heat.

All technical advice, recommendations and services are rendered by the seller gratis. They are based on technical data which they believe to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for the results obtained or damages incurred from their use by Buyer in whole or part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.
