



VOC CHART

Revision 20260217

DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GlobalStar Toners (EZMIX)								
BLACK	73.65	1.054	8.795	0.00	277.710	2.318	277.710	2.318
MEDIUM YELLOW	75.61	1.118	9.329	0.00	272.608	2.275	272.608	2.275
LEMON YELLOW HS	66.99	1.206	10.063	0.00	398.108	3.322	398.108	3.322
WARM YELLOW HS	63.32	1.153	9.624	0.00	422.951	3.530	422.951	3.530
ORGANIC ORANGE	59.83	1.036	8.644	0.00	416.104	3.473	416.104	3.473
LEMON YELLOW	58.74	1.062	8.866	0.00	438.343	3.658	438.343	3.658
ORANGE	57.93	1.049	8.756	0.00	441.422	3.684	441.422	3.684
FUCHSIA RED	42.97	0.987	8.239	0.00	563.016	4.699	563.016	4.699
DEEP BLACK	65.21	1.037	8.651	0.00	360.637	3.010	360.637	3.010
GREEN	57.20	1.047	8.741	0.00	448.339	3.742	448.339	3.742
OCHRE YELLOW	80.96	1.667	13.915	0.00	317.418	2.649	317.418	2.649
BLUE	61.33	1.040	8.682	0.00	402.308	3.357	402.308	3.357
VIOLET	59.04	1.010	8.433	0.00	413.934	3.454	413.934	3.454
LIGHT RED	73.09	1.138	9.493	0.00	306.144	2.555	306.144	2.555
TITANIUM WHITE	91.82	1.886	15.738	0.00	154.202	1.287	154.202	1.287
SCARLET RED	65.60	1.087	9.067	0.00	373.732	3.119	373.732	3.119
AMARANTH VIOLET	57.69	1.037	8.650	0.00	438.560	3.660	438.560	3.660
ALPHA PTHALO BLUE	58.61	1.040	8.678	0.00	430.395	3.592	430.395	3.592
TRANSPARENT RED OXIDE	59.07	1.068	8.916	0.00	437.254	3.649	437.254	3.649
TRANSPARENT YELLOW OXIDE	61.92	1.100	9.178	0.00	418.763	3.495	418.763	3.495
MEDIUM SILVER DOLLAR ALUMINUM (HV)	44.25	1.040	8.676	0.00	579.551	4.836	579.551	4.836
COARSE ALUMINUM (HV)	52.41	1.051	8.773	0.00	500.256	4.175	500.256	4.175
GlobalBase Toners								
OXIDE RED	84.87	1.868	15.590	0.00	282.587	2.358	282.587	2.358
LEMON YELLOW	85.28	1.709	14.260	0.00	251.536	2.099	251.536	2.099
FINE ALUMINUM	48.92	1.044	8.711	2.00	513.660	4.287	512.298	4.275
COARSE LENTICULAR ALUMINUM (HV)	43.62	1.039	8.673	0.00	585.961	4.890	585.961	4.890
MAGNUM SILVER DOLLAR ALUMINUM (HV)	52.69	1.084	9.047	0.00	512.897	4.280	512.897	4.280
EXTRA FINE ALUMINUM (HV)	48.10	1.044	8.709	0.00	541.602	4.520	541.602	4.520
MEDIUM ALUMINUM	44.10	1.05	8.76	0.00	587.000	4.900	587.000	4.900
BASE EXTRA COARSE ALUMINUM	48.92	1.044	8.711	2.00	513.660	4.287	512.298	4.275
BASE ALUMINUM EXTRA FINE	42.50	1.020	8.510	0.00	587.000	4.900	587.000	4.900
BASE MICRO WHITE	33.00	1.080	9.010	0.00	724.000	6.040	724.000	6.040
BASE WHITE PEARL	45.46	1.065	8.887	0.00	580.786	4.847	580.786	4.847
BASE FINE WHITE PEARL	45.46	1.078	8.993	0.00	587.721	4.905	587.721	4.905
BLUE PEARL	45.46	1.078	8.995	0.00	587.816	4.905	587.816	4.905
GREEN PEARL	46.42	1.077	8.989	0.00	577.132	4.816	577.132	4.816
VIOLET PEARL	45.46	1.080	9.010	0.00	588.794	4.914	588.794	4.914
YELLOW PEARL	45.46	1.076	8.982	0.00	586.959	4.898	586.959	4.898
RED PEARL	45.46	1.081	9.023	0.00	589.661	4.921	589.661	4.921

DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
Binders								
HIGH GLOSS FAST AIR DRY ALKYD	47.01	0.981	8.186	0.00	519.828	4.338	519.828	4.338
LOW VOC ACRYLIC ALKYD	42.94	1.155	9.642	38.10	326.391	2.724	219.091	1.828
MS LOW VOC ACRYLIC POLYURETHANE	43.55	1.080	9.016	39.14	297.710	2.484	187.002	1.561
MS SATIN LOW VOC ACRYLIC POLYURETHANE BINDER	31.64	0.993	8.285	57.41	290.252	2.422	108.700	0.907
HIGH GLOSS MS ACRYLIC POLYURETHANE	47.47	0.976	8.148	20.01	432.970	3.613	317.566	2.650
UHS LOW VOC POLYURETHANE	41.21	1.125	9.390	44.48	273.463	2.282	161.075	1.344
HIGH GLOSS UHS POLYURETHANE	51.25	0.986	8.232	7.79	447.882	3.738	404.019	3.372
LOW VOC BASECOAT BINDER	16.33	1.193	9.959	76.37	322.044	2.688	87.117	0.727
BASECOAT BINDER	13.96	0.884	7.375	0.00	760.355	6.345	760.355	6.345
DTM BINDER	55.18	0.967	8.072	8.53	392.216	3.273	350.958	2.929
FLAT DTM BINDER	62.28	1.065	8.884	6.84	362.336	3.024	328.699	2.743
DTM LOW VOC BINDER	52.27	1.010	8.426	28.38	274.619	2.292	195.338	1.630
DTM LOW VOC FLAT BINDER	56.00	1.123	9.369	28.15	244.857	2.043	178.007	1.486
GlobalBase Binder								
LOW VOC GLOBALBASE BINDER	16.33	1.193	9.959	76.37	322.044	2.688	87.117	0.727
GLOBALBASE BINDER	13.96	0.884	7.375	0.00	760.355	6.345	760.355	6.345
GlobalBase Clear Coats and Primers								
GLOBALBASE NATIONAL RULE 4:1 CLEAR	37.99	0.936	7.810	28.70	456.780	3.812	311.749	2.602
GLOBALBASE LOW VOC 4:1 CLEAR	29.09	1.105	9.225	59.78	284.383	2.373	122.992	1.026
GLOBALBASE NATIONAL RULE 2:1 CLEAR	43.27	0.973	8.118	28.48	398.397	3.323	274.883	2.264
GLOBALBASE LOW VOC 2:1 CLEAR	39.83	1.056	8.813	43.86	300.543	2.508	172.255	1.438
GLOBALBASE PRIMER	60.13	1.366	11.400	6.58	507.726	4.237	454.873	3.796
FAST ACTIVATOR	30.05	0.948	7.915	0.00	663.452	5.537	663.452	5.537
MEDIUM ACTIVATOR	30.03	0.934	7.795	0.00	653.564	5.454	653.564	5.454
SLOW ACTIVATOR	30.02	0.962	8.032	0.00	673.523	5.621	673.523	5.621
FAST LOW VOC ACTIVATOR	31.35	1.136	9.482	66.55	71.784	0.599	23.993	0.200
MEDIUM LOW VOC ACTIVATOR	29.80	1.195	9.975	68.19	71.784	0.599	23.993	0.200
SLOW LOW VOC ACTIVATOR	28.01	1.272	10.611	70.10	71.784	0.599	23.993	0.200
GlobalStar Primers								
1K LV DTM PRIMER	52.25	1.567	13.076	39.20	247.583	2.066	134.000	1.118
1K GRAY DTM PRIMER	59.15	1.287	10.738	0.00	525.617	4.386	525.617	4.386
HS GRAY EPOXY PRIMER	64.83	1.304	10.885	0.00	458.686	3.828	458.686	3.828
DTM 2K POLYURETHANE LOW VOC PRIMER	60.23	1.428	11.916	27.33	277.047	2.312	177.664	1.483
DTM 2K POLYURETHANE LOW VOC PRIMER	67.43	1.358	11.332	8.53	382.963	3.196	326.461	2.724
HS GRAY EPOXY PRIMER	66.39	1.294	10.798	22.99	214.770	1.792	137.401	1.147

DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
Hardeners, Activators, Thinners & Miscellaneous								
HARDENER FOR 3G, 6B, L5 AND P7	50.01	0.970	8.095	0.00	484.954	4.047	484.954	4.047
SLOW ACTIVATOR	50.01	0.970	8.095	0.00	484.954	4.047	484.954	4.047
HARDENER FOR L7-SERIES	81.00	1.075	8.972	0.00	204.273	1.705	204.273	1.705
HARDENER FOR L2, L4, L6, AND L10	80.00	1.192	9.946	20.00	0.000	0.000	0.000	0.000
HARDENER FOR LC, P12 AND L12	38.21	1.264	10.552	61.79	0.000	0.000	0.000	0.000
QUICK EPOXY HARDENER FOR P9-SERIES	37.48	0.926	7.726	44.89	333.310	2.782	163.230	1.362
QUICK EPOXY HARDENER FOR P12-SERIES	32.32	1.073	8.956	60.52	197.958	1.652	76.792	0.641
FAST PU REDUCER	0.00	0.839	7.004	9.00	848.601	7.082	763.741	6.374
MEDIUM PU REDUCER	0.00	0.852	7.110	0.00	851.997	7.110	851.997	7.110
SLOW PU REDUCER	0.00	0.868	7.240	0.00	867.569	7.240	867.569	7.240
FAST ZERO VOC PU REDUCER	0.00	0.785	6.550	100.00	0.000	0.000	0.000	0.000
MEDIUM ZERO VOC PU REDUCER	0.00	1.061	8.855	100.00	0.000	0.000	0.000	0.000
SLOW ZERO VOC PU REDUCER	0.00	1.339	11.173	100.00	0.000	0.000	0.000	0.000