

GlobalStar

6B.1.K1

High Gloss DTM

Industrial Acrylic Polyurethane →

EU/ROW082320166B.1.K1

Technical Data Sheet

Description

6B.1.K1 is a two pack acrylic urethane DTM topcoat created for painting of all types of ferrous metals. Care must be taken in surface preparation when DTM applications are used. An appropriate primer is always the best way to insure a longer life and finer finish.

Suggested Uses

As a high performance topcoat over suitable primers or over properly prepared substrates, including: Hot and Cold roll steel, Galvanized Steel, Aluminum, fiberglass, plastics and wood where:

- Outstanding Gloss and color retention are desired.
- Outstanding adhesion and flexibility is required.
- Excellent DOI and leveling is required.
- Excellent performance when using air-assist airless, pressure pot, cup gun.
- Can be applied in small areas with roller or brush.

Field Applications

- Heavy industrial equipment
- Oil Field equipment
- Construction equipment
- Airport ground support equipment
- Truck and Trailer Refinishing

Components

6B.1. K1

OG.013

OG.030

OA.014

Base

Polyurethane Reducer Standard

Polyurethane Reducer Slow

Hardener

GlobalStar Industrial

GlobalStar

6B.1.K1

High Gloss DTM

Industrial Acrylic Polyurethane →

EU/ROW082320166B.1.K1

Mixing Ratio

Mix:

Mix three (3) parts base color to one (1) part OA.014 hardener.
Reduce up to 20% with Selected Reducer.

Pot Life

4 hours @ 20° C (68° F)

Application

Apply:

Two medium wet coats, allow 10-20 minutes flash between coats.

Spray Gun:

HVLP Gravity Feed – 1.4 – 1.6mm tip and needle
Pressure Pot HVLP – 1.0 – 1.1mm tip and needle
Air Assist Airless - 1.0 – 1.1mm tip and needle
Conventional – 1.4 – 1.7mm tip and needle
Airless Not recommended.

Film Build:

60-90 microns – (2.4 – 3.6 mils.) when applied.

Dry Times

Dust Free:

15-30 minutes @ 20° C (68° F)

Dry to Touch

2-4 hours @ 20° C (68° F)

Total Hardness

24 hours @ 20° C (68° F)

Force Dry

30 minutes @ 60° C (140° F)

Chemical Resistance

Maximum resistance after 7 days

Surface Preparation

Ferrous metals:

Best Case

SA2 sandblast Blow all dust and contaminants off and apply Globalstar primer followed by topcoat.

Second Best Case

Hot Phosphate wash system, blow dry and apply Globalstar primer followed by topcoat.

GlobalStar

6B.1.K1

High Gloss DTM

Industrial Acrylic Polyurethane →

EU/ROW082320166B.1.K1

Third Best Case

Careful mechanical abrasion. Clean all dust, oil residue, finger prints and contaminants before and after mechanical abrasion with a clean drying wax and grease removal solvent making sure all residue is removed. Blow dry and apply Globalstar primer followed by topcoat. Apply topcoat within 8 hours.

Aluminum:

Clean surface with clean drying wax and grease remover. Apply suitable Globalstar Epoxy Primer followed by topcoat as recommended.

Galvanized Steel:

Clean all dust, oil residue, and contaminants from surface using a clean drying wax and grease remover. Light Sanding (320P grit). Clean again with clean drying wax and grease remover using a wipe and dry process. Apply Globalstar Epoxy Primer follow by topcoat as recommended.

VOC

Regulatory VOC National Rule
Actual VOC National Rule

500.0 g/l (4.17 lbs./gl.)
500.0 g/l (4.17 lbs./gl.)

Solids

By Volume
By Weight

40%
60%

Specific Gravity

1.23 kg/l (9.5 lbs./gl.)

Coverage

353.1 square feet per gallon @ 100% transfer efficiency, 50 microns (2 mils)
32.78 square meters per gallon@ 100% transfer efficiency, 50 microns (2 mils)

GlobalStar Industrial

GlobalStar

6B.1.K1

High Gloss DTM

Industrial Acrylic Polyurethane →

EU/ROW082320166B.1.K1

Salt Spray Test

(ASTM B 117)

200 hours with dry film of 80 microns (3.1 mils.)
Sprayed directly on bare sand blasted steel.

Impact Test

(ASTM D 2794)

36 kg direct, 10 kg reverse, on sanded steel. (Passed).

Yellowing

(ASTM D 4587)

After 1000 hours $\Delta E \leq 3$ (with 2% of 03.007 anti UV additive inside)

Repainting

Can be recoated up to 6 hours from application, after 24 hours light sanding recommended for best adhesion. After force dry recommendations are completed light sanding is recommended →

Storage Stability

One year for A (base) component, 6 months B (Hardener)
Component in closed package, in cool dry place, away from any heat source.

Heat Resistance

Once cured 180° C (356° F)

Chemical Resistance:

Test	Results	Cure Time
HCl Solution 10%	4	7 days
HNO ₃ Solution 10%	2	7 days
H ₂ SO ₄ Solution 10%	4	7 days
Acetic acid solution 10%	5-4	7 days
Mix of NaCl 10%, Lactic acid 5%	5-4	7 days
Synthetic sweat	5	7 days
H ₂ O ₂ 35%	1	7 days

GlobalStar

6B.1.K1

High Gloss DTM

Industrial Acrylic Polyurethane →

EU/ROW082320166B.1.K1

NH ₃ Solution 30%	5	7 days
NaOH Solution 10%	5	7 days
Acetone	4-3	7 days
Cyclohexanone	1	7 days
HiSol 100	4-3	7 days
Ethyl Acetate	4-3	7 days
Ethanol	4-3	7 days
Synthetic oil	4	7 days
Hydraulic oil	5	7 days
Transmission oil SEA 30	5	7 days
Engine oil 15W40	5	7 days
Viakal	5	7 days
Unleaded gasoline	5	7 days

All Technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.