



GLOBALSTAR VOC CHART

Revision 20260818

	CODE	DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GlobalStar Toners (EZMIX)										
	OH4.028	BLACK	73.65	1.05	8.79	0.00	277.71	2.32	277.71	2.32
	OH4.101	MEDIUM YELLOW	75.61	1.12	9.33	0.00	272.61	2.27	272.61	2.27
	OH4.102	LEMON YELLOW HS	66.99	1.21	10.06	0.00	398.11	3.32	398.11	3.32
	OH4.103	WARM YELLOW HS	63.32	1.15	9.62	0.00	422.95	3.53	422.95	3.53
	OH4.108	ORGANIC ORANGE	59.83	1.04	8.64	0.00	416.10	3.47	416.10	3.47
	OH4.112	LEMON YELLOW	58.74	1.06	8.87	0.00	438.34	3.66	438.34	3.66
	OH4.114	ORANGE	57.93	1.05	8.76	0.00	441.42	3.68	441.42	3.68
	OH4.119	FUCHSIA RED	42.97	0.99	8.24	0.00	563.02	4.70	563.02	4.70
	OH4.120	DEEP BLACK	65.21	1.04	8.65	0.00	360.64	3.01	360.64	3.01
	OH4.124	GREEN	57.20	1.05	8.74	0.00	448.34	3.74	448.34	3.74
	OH4.125	OCHRE YELLOW	80.96	1.67	13.91	0.00	317.42	2.65	317.42	2.65
	OH4.126	BLUE	61.33	1.04	8.68	0.00	402.31	3.36	402.31	3.36
	OH4.127	VIOLET	59.04	1.01	8.43	0.00	413.93	3.45	413.93	3.45
	OH4.129	LIGHT RED	73.09	1.14	9.49	0.00	306.14	2.55	306.14	2.55
	OH4.130	TITANIUM WHITE	91.82	1.89	15.74	0.00	154.20	1.29	154.20	1.29
	OH4.132	SCARLET RED	65.60	1.09	9.07	0.00	373.73	3.12	373.73	3.12
	OH4.133	AMARANTH VIOLET	57.69	1.04	8.65	0.00	438.56	3.66	438.56	3.66
	OH4.134	ALPHA PTHALO BLUE	58.61	1.04	8.68	0.00	430.40	3.59	430.40	3.59
	OH4.TR029	TRANSPARENT RED OXIDE	59.07	1.07	8.92	0.00	437.25	3.65	437.25	3.65
	OH4.TR030	TRANSPARENT YELLOW OXIDE	61.92	1.10	9.18	0.00	418.76	3.49	418.76	3.49
	OD7.037	MEDIUM SILVER DOLLAR ALUMINUM (HV)	44.25	1.04	8.68	0.00	579.55	4.84	579.55	4.84
	OD7.044	COARSE ALUMINUM (HV)	52.41	1.05	8.77	0.00	500.26	4.17	500.26	4.17



GLOBALSTAR VOC CHART

	CODE	DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GlobalBase Toners	0H4.122	OXIDE RED	84.87	1.87	15.59	0.00	282.59	2.36	282.59	2.36
	0H4.204	LEMON YELLOW	85.28	1.71	14.26	0.00	251.54	2.10	251.54	2.10
	0D7.066	FINE ALUMINUM	48.92	1.04	8.71	2.00	513.66	4.29	512.30	4.28
	0D7.077	COARSE LENTICULAR ALUMINUM (HV)	43.62	1.04	8.67	0.00	585.96	4.89	585.96	4.89
	0D7.012	MAGNUM SILVER DOLLAR ALUMINUM (HV)	52.69	1.08	9.05	0.00	512.90	4.28	512.90	4.28
	0D7.050	EXTRA FINE ALUMINUM (HV)	48.10	1.04	8.71	0.00	541.60	4.52	541.60	4.52
	0D7.067	MEDIUM ALUMINUM	44.10	1.05	8.76	0.00	587.00	4.90	587.00	4.90
	0D7.069	BASE EXTRA COARSE ALUMINUM	48.92	1.04	8.71	2.00	513.66	4.29	512.30	4.28
	0D7.074	BASE ALUMINUM EXTRA FINE	42.50	1.02	8.51	0.00	587.00	4.90	587.00	4.90
	0D7.230	BASE MICRO WHITE	33.00	1.08	9.01	0.00	724.00	6.04	724.00	6.04
	0D7.401	BASE WHITE PEARL	45.46	1.06	8.89	0.00	580.79	4.85	580.79	4.85
	0D7.402	BASE FINE WHITE PEARL	45.46	1.08	8.99	0.00	587.72	4.90	587.72	4.90
	0D7.403	BLUE PEARL	45.46	1.08	8.99	0.00	587.82	4.91	587.82	4.91
	0D7.404	GREEN PEARL	46.42	1.08	8.99	0.00	577.13	4.82	577.13	4.82
	0D7.405	VIOLET PEARL	45.46	1.08	9.01	0.00	588.79	4.91	588.79	4.91
	0D7.406	YELLOW PEARL	45.46	1.08	8.98	0.00	586.96	4.90	586.96	4.90
	0D7.407	RED PEARL	45.46	1.08	9.02	0.00	589.66	4.92	589.66	4.92
Binders	7D.1.K1	HIGH GLOSS FAST AIR DRY ALKYD	47.01	0.98	8.19	0.00	519.83	4.34	519.83	4.34
	L2.1.K2	LOW VOC ACRYLIC ALKYD	42.94	1.16	9.64	38.10	326.39	2.72	219.09	1.83
	L4.1.K1	MS LOW VOC ACRYLIC POLYURETHANE	43.55	1.08	9.02	39.14	297.71	2.48	187.00	1.56
	L4.4.K1	MS SATIN LOW VOC ACRYLIC POLYURETHANE BINE	31.64	0.99	8.28	57.41	290.25	2.42	108.70	0.91
	L5.1.K1	HIGH GLOSS MS ACRYLIC POLYURETHANE	48.37	0.98	8.14	0.00	503.67	4.20	503.67	4.20
	L6.1.K1	UHS LOW VOC POLYURETHANE	41.21	1.13	9.39	44.48	273.46	2.28	161.07	1.34
	L7.1.K1	HIGH GLOSS UHS POLYURETHANE	51.25	0.99	8.23	7.79	447.88	3.74	404.02	3.37
	L8.3.K2	LOW VOC BASECOAT BINDER	16.33	1.19	9.96	76.37	322.04	2.69	87.12	0.73
	L9.3.K1	BASECOAT BINDER	13.96	0.88	7.37	0.00	760.39	6.35	760.39	6.35
	L11.1.K1	DTM BINDER	50.48	0.97	8.10	7.80	448.17	3.74	404.92	3.38
	L11.4.K1	FLAT DTM BINDER	56.05	1.04	8.64	6.55	426.82	3.54	387.17	3.23
	L12.1.K1	DTM LOW VOC BINDER	47.41	1.01	8.42	26.59	359.43	3.00	262.23	2.19
	L12.4.K1	DTM LOW VOC FLAT BINDER	51.33	1.11	9.27	26.97	325.66	2.72	241.35	2.01



GLOBALSTAR VOC CHART

	CODE	DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GlobalBase Binder										
	LB8	LOW VOC GLOBALBASE BINDER	16.33	1.19	9.96	76.37	322.04	2.69	87.12	0.73
	LB9	GLOBALBASE BINDER	13.96	0.88	7.37	0.00	760.39	6.35	760.39	6.35
GlobalBase Clear Coats and Primers										
	LC3030	GLOBALBASE NATIONAL RULE 4:1 CLEAR	37.99	0.94	7.81	28.70	456.78	3.81	311.75	2.60
	LC3030LV	GLOBALBASE LOW VOC 4:1 CLEAR	29.09	1.11	9.23	59.78	284.38	2.37	122.99	1.03
	LC2010	GLOBALBASE NATIONAL RULE 2:1 CLEAR	43.26	0.97	8.12	28.48	398.40	3.32	274.99	2.29
	LC2010LV	GLOBALBASE LOW VOC 2:1 CLEAR	39.83	1.06	8.81	43.86	300.54	2.51	172.25	1.44
	LP3030HS	GLOBALBASE PRIMER	60.13	1.37	11.40	6.57	507.73	4.24	454.87	3.80
	LH60	FAST ACTIVATOR	30.05	0.95	7.91	0.00	663.45	5.54	663.45	5.54
	LH70	MEDIUM ACTIVATOR	30.03	0.93	7.80	0.00	653.56	5.45	653.56	5.45
	LH85	SLOW ACTIVATOR	30.02	0.96	8.03	0.00	673.52	5.62	673.52	5.62
	LH060	FAST LOW VOC ACTIVATOR	31.35	1.14	9.49	66.54	71.78	0.60	24.01	0.20
	LH070	MEDIUM LOW VOC ACTIVATOR	29.80	1.20	9.98	68.19	71.78	0.60	24.00	0.20
	LH085	SLOW LOW VOC ACTIVATOR	28.01	1.27	10.61	70.10	71.78	0.60	23.99	0.20
GlobalStar Primers										
	P6.3.K1	1K LV DTM PRIMER	52.25	1.57	13.08	39.20	247.58	2.07	134.00	1.12
	P8.3.K1	1K GRAY DTM PRIMER	59.15	1.29	10.74	0.00	525.62	4.39	525.62	4.39
	P9.3.K1	HS GRAY EPOXY PRIMER	64.83	1.30	10.89	0.00	458.69	3.83	458.69	3.83
	P10.3.K1	DTM 2K POLYURETHANE LOW VOC PRIMER	60.23	1.43	11.92	27.33	277.05	2.31	177.66	1.48
	P11.3.K1	DTM 2K POLYURETHANE LOW VOC PRIMER	64.87	1.34	11.18	8.21	419.56	3.50	360.78	3.01
	P12.3.K1	HS GRAY EPOXY PRIMER	66.39	1.29	10.80	22.99	214.77	1.79	137.40	1.15



GLOBALSTAR VOC CHART

		CODE	DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
Hardeners, Activators, Thinners & Miscellaneous		AE.002	HARDENER FOR 3G, 6B, L5 AND P7	50.01	0.97	8.10	0.00	484.95	4.05	484.95	4.05
		AE.002.SLOW	SLOW ACTIVATOR	50.01	0.97	8.10	0.00	484.95	4.05	484.95	4.05
		AH.002	HARDENER FOR L7-SERIES	81.00	1.08	8.97	0.00	204.27	1.70	204.27	1.70
		AV.002	HARDENER FOR L2, L4, L6, AND L10	80.00	1.19	9.95	20.00	0.00	0.00	0.00	0.00
		AV.005	HARDENER FOR LC, P12 AND L12	38.21	1.26	10.55	61.79	0.00	0.00	0.00	0.00
		EH.001	QUICK EPOXY HARDENER FOR P9-SERIES	37.48	0.93	7.73	44.89	333.31	2.78	163.23	1.36
		EH.001LV	QUICK EPOXY HARDENER FOR P12-SERIES	32.32	1.07	8.96	60.52	197.96	1.65	76.79	0.64
		GSR-F	FAST PU REDUCER	0.00	0.84	7.00	9.00	848.60	7.08	763.74	6.37
		GSR-M	MEDIUM PU REDUCER	0.00	0.85	7.11	0.00	852.00	7.11	852.00	7.11
		GSR-S	SLOW PU REDUCER	0.00	0.87	7.24	0.00	867.57	7.24	867.57	7.24
		GSOR-F	FAST ZERO VOC PU REDUCER	0.00	0.78	6.55	100.00	0.00	0.00	0.00	0.00
		GSOR-M	MEDIUM ZERO VOC PU REDUCER	0.00	1.06	8.86	100.00	0.00	0.00	0.00	0.00
		GSOR-S	SLOW ZERO VOC PU REDUCER	0.00	1.34	11.17	100.00	0.00	0.00	0.00	0.00