



VOC CHART

Revision 20251024

	CODE	DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GlobalStar Toners (EZMIX)										
	0H4.028	BLACK	73.65	1.054	8.795	0.00	277.710	2.318	277.710	2.318
	0H4.101	MEDIUM YELLOW	75.61	1.118	9.329	0.00	272.608	2.275	272.608	2.275
	0H4.102	LEMON YELLOW HS	66.99	1.206	10.063	0.00	398.108	3.322	398.108	3.322
	0H4.103	WARM YELLOW HS	63.32	1.153	9.624	0.00	422.951	3.530	422.951	3.530
	0H4.108	ORGANIC ORANGE	59.83	1.036	8.644	0.00	416.104	3.473	416.104	3.473
	0H4.112	LEMON YELLOW	58.74	1.062	8.866	0.00	438.343	3.658	438.343	3.658
	0H4.114	ORANGE	57.93	1.049	8.756	0.00	441.422	3.684	441.422	3.684
	0H4.119	FUCHSIA RED	42.97	0.987	8.239	0.00	563.016	4.699	563.016	4.699
	0H4.120	DEEP BLACK	65.21	1.037	8.651	0.00	360.637	3.010	360.637	3.010
	0H4.124	GREEN	57.20	1.047	8.741	0.00	448.339	3.742	448.339	3.742
	0H4.125	OCHRE YELLOW	80.96	1.667	13.915	0.00	317.418	2.649	317.418	2.649
	0H4.126	BLUE	61.33	1.040	8.682	0.00	402.308	3.357	402.308	3.357
	0H4.127	VIOLET	59.04	1.010	8.433	0.00	413.934	3.454	413.934	3.454
	0H4.129	LIGHT RED	73.09	1.138	9.493	0.00	306.144	2.555	306.144	2.555
	0H4.130	TITANIUM WHITE	91.82	1.886	15.738	0.00	154.202	1.287	154.202	1.287
	0H4.132	SCARLET RED	65.60	1.087	9.067	0.00	373.732	3.119	373.732	3.119
	0H4.133	AMARANTH VIOLET	57.69	1.037	8.650	0.00	438.560	3.660	438.560	3.660
	0H4.134	ALPHA PTHALO BLUE	58.61	1.040	8.678	0.00	430.395	3.592	430.395	3.592
	0H4.TR029	TRANSPARENT RED OXIDE	59.07	1.068	8.916	0.00	437.254	3.649	437.254	3.649
	0H4.TR030	TRANSPARENT YELLOW OXIDE	61.92	1.100	9.178	0.00	418.763	3.495	418.763	3.495
	0D7.037	MEDIUM SILVER DOLLAR ALUMINUM (HV)	44.25	1.040	8.676	0.00	579.551	4.836	579.551	4.836
	0D7.044	COARSE ALUMINUM (HV)	52.41	1.051	8.773	0.00	500.256	4.175	500.256	4.175
GlobalBase Toners										
	0H4.122	OXIDE RED	84.87	1.868	15.590	0.00	282.587	2.358	282.587	2.358
	0H4.204	LEMON YELLOW	85.28	1.709	14.260	0.00	251.536	2.099	251.536	2.099
	0D7.066	FINE ALUMINUM	48.92	1.044	8.711	2.00	513.660	4.287	512.298	4.275
	0D7.077	COARSE LENTICULAR ALUMINUM (HV)	43.62	1.039	8.673	0.00	585.961	4.890	585.961	4.890
	0D7.012	MAGNUM SILVER DOLLAR ALUMINUM (HV)	52.69	1.084	9.047	0.00	512.897	4.280	512.897	4.280
	0D7.050	EXTRA FINE ALUMINUM (HV)	48.10	1.044	8.709	0.00	541.602	4.520	541.602	4.520
	0D7.067	MEDIUM ALUMINUM	44.10	1.05	8.76	0.00	587.000	4.900	587.000	4.900
	0D7.069	BASE EXTRA COARSE ALUMINUM	48.92	1.044	8.711	2.00	513.660	4.287	512.298	4.275
	0D7.074	BASE ALUMINUM EXTRA FINE	42.50	1.020	8.510	0.00	587.000	4.900	587.000	4.900
	0D7.230	BASE MICRO WHITE	33.00	1.080	9.010	0.00	724.000	6.040	724.000	6.040
	0D7.401	BASE WHITE PEARL	45.46	1.065	8.887	0.00	580.786	4.847	580.786	4.847
	0D7.402	BASE FINE WHITE PEARL	45.46	1.078	8.993	0.00	587.721	4.905	587.721	4.905
	0D7.403	BLUE PEARL	45.46	1.078	8.995	0.00	587.816	4.905	587.816	4.905
	0D7.404	GREEN PEARL	46.42	1.077	8.989	0.00	577.132	4.816	577.132	4.816
	0D7.405	VIOLET PEARL	45.46	1.080	9.010	0.00	588.794	4.914	588.794	4.914
	0D7.406	YELLOW PEARL	45.46	1.076	8.982	0.00	586.959	4.898	586.959	4.898
	0D7.407	RED PEARL	45.46	1.081	9.023	0.00	589.661	4.921	589.661	4.921

	CODE	DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
Binders	7D.1.K1	HIGH GLOSS FAST AIR DRY ALKYD	47.01	0.981	8.186	0.00	519.828	4.338	519.828	4.338
	L2.1.K2	LOW VOC ACRYLIC ALKYD	42.94	1.155	9.642	38.10	326.391	2.724	219.091	1.828
	L4.1.K1	MS LOW VOC ACRYLIC POLYURETHANE	43.55	1.080	9.016	39.14	297.710	2.484	187.002	1.561
	L4.4.K1	MS SATIN LOW VOC ACRYLIC POLYURETHANE BIN	31.64	0.993	8.285	57.41	290.252	2.422	108.700	0.907
	L5.1.K1	HIGH GLOSS MS ACRYLIC POLYURETHANE	47.47	0.976	8.148	20.01	432.970	3.613	317.566	2.650
	L6.1.K1	UHS LOW VOC POLYURETHANE	41.21	1.125	9.390	44.48	273.463	2.282	161.075	1.344
	L7.1.K1	HIGH GLOSS UHS POLYURETHANE	51.25	0.986	8.232	7.79	447.882	3.738	404.019	3.372
	L8.3.K2	LOW VOC BASECOAT BINDER	16.33	1.193	9.959	76.37	322.044	2.688	87.117	0.727
	L9.3.K1	BASECOAT BINDER	13.96	0.884	7.375	0.00	760.355	6.345	760.355	6.345
	L11.1.K1	DTM BINDER	55.18	0.967	8.072	8.53	392.216	3.273	350.958	2.929
	L11.4.K1	FLAT DTM BINDER	62.28	1.065	8.884	6.84	362.336	3.024	328.699	2.743
	L12.1.K1	DTM LOW VOC BINDER	52.27	1.010	8.426	28.38	274.619	2.292	195.338	1.630
	L12.4.K1	DTM LOW VOC FLAT BINDER	56.00	1.123	9.369	28.15	244.857	2.043	178.007	1.486
GlobalBase Binder	LB8	LOW VOC GLOBALBASE BINDER	16.33	1.193	9.959	76.37	322.044	2.688	87.117	0.727
	LB9	GLOBALBASE BINDER	13.96	0.884	7.375	0.00	760.355	6.345	760.355	6.345
GlobalBase Clear Coats and Primers										
Check	LC3030	GLOBALBASE NATIONAL RULE 4:1 CLEAR	37.99	0.936	7.810	28.70	456.780	3.812	311.749	2.602
	LC3030LV	GLOBALBASE LOW VOC 4:1 CLEAR	29.09	1.105	9.225	59.78	284.383	2.373	122.992	1.026
	LC2010	GLOBALBASE NATIONAL RULE 4:1 CLEAR	43.27	0.973	8.118	28.48	398.397	3.323	274.883	2.264
	LC2010LV	GLOBALBASE LOW VOC 2:1 CLEAR	39.83	1.056	8.813	43.86	300.543	2.508	172.255	1.438
	LP3030HS	GLOBALBASE PRIMER	60.13	1.366	11.400	6.58	507.726	4.237	454.873	3.796
	LH60	FAST ACTIVATOR	30.05	0.948	7.915	0.00	663.452	5.537	663.452	5.537
	LH70	MEDIUM ACTIVATOR	30.03	0.934	7.795	0.00	653.564	5.454	653.564	5.454
	LH85	SLOW ACTIVATOR	30.02	0.962	8.032	0.00	673.523	5.621	673.523	5.621
	LH060	FAST LOW VOC ACTIVATOR	31.35	1.136	9.482	66.55	71.784	0.599	23.993	0.200
	LH070	MEDIUM LOW VOC ACTIVATOR	29.80	1.195	9.975	68.19	71.784	0.599	23.993	0.200
	LH085	SLOW LOW VOC ACTIVATOR	28.01	1.272	10.611	70.10	71.784	0.599	23.993	0.200
GlobalStar Primers										
	P6.3.K1	1K LV DTM PRIMER	52.25	1.567	13.076	39.20	247.583	2.066	134.000	1.118
	P8.3.K1	1K GRAY DTM PRIMER	59.15	1.287	10.738	0.00	525.617	4.386	525.617	4.386
	P9.3.K1	HS GRAY EPOXY PRIMER	64.83	1.304	10.885	0.00	458.686	3.828	458.686	3.828
	P10.3.K1	DTM 2K POLYURETHANE LOW VOC PRIMER	60.23	1.428	11.916	27.33	277.047	2.312	177.664	1.483
	P11.3.K1	DTM 2K POLYURETHANE LOW VOC PRIMER	67.43	1.358	11.332	8.53	382.963	3.196	326.461	2.724
	P12.3.K1	HS GRAY EPOXY PRIMER	66.39	1.294	10.798	22.99	214.770	1.792	137.401	1.147

	CODE	DESCRIPTION	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
Hardeners, Activators, Thinners & Miscellaneous										
	AE.002	HARDENER FOR 3G, 6B, L5 AND P7	50.01	0.970	8.095	0.00	484.954	4.047	484.954	4.047
	AE.002.SLOW	SLOW ACTIVATOR	50.01	0.970	8.095	0.00	484.954	4.047	484.954	4.047
	AH.002	HARDENER FOR L7-SERIES	81.00	1.075	8.972	0.00	204.273	1.705	204.273	1.705
	AV.002	HARDENER FOR L2, L4, L6, AND L10	80.00	1.192	9.946	20.00	0.000	0.000	0.000	0.000
	AV.005	HARDENER FOR LC, P12 AND L12	38.21	1.264	10.552	61.79	0.000	0.000	0.000	0.000
	EH.001	QUICK EPOXY HARDENER FOR P9-SERIES	37.48	0.926	7.726	44.89	333.310	2.782	163.230	1.362
	EH.001LV	QUICK EPOXY HARDENER FOR P12-SERIES	32.32	1.073	8.956	60.52	197.958	1.652	76.792	0.641
	GSR-F	FAST PU REDUCER	0.00	0.839	7.004	9.00	848.601	7.082	763.741	6.374
	GSR-M	MEDIUM PU REDUCER	0.00	0.852	7.110	0.00	851.997	7.110	851.997	7.110
	GSR-S	SLOW PU REDUCER	0.00	0.868	7.240	0.00	867.569	7.240	867.569	7.240
	GSOR-F	FAST ZERO VOC PU REDUCER	0.00	0.785	6.550	100.00	0.000	0.000	0.000	0.000
	GSOR-M	MEDIUM ZERO VOC PU REDUCER	0.00	1.061	8.855	100.00	0.000	0.000	0.000	0.000
	GSOR-S	SLOW ZERO VOC PU REDUCER	0.00	1.339	11.173	100.00	0.000	0.000	0.000	0.000