

**GlobalStar**

6H.1.K1

High Gloss

MS Acrylic Polyurethane

EU/ROW082320166H.1.K1

## Technical Data Sheet

### Description

6H.1.K1 is a two pack medium solids high gloss urethane topcoat created for painting of all types of substrates on manufactured items, and refinish projects.

### Suggested Uses

As a high performance topcoat over properly prepared primed or sealed substrates and sanded stable coatings, including: Hot and Cold roll steel, Galvanized Steel, Aluminum, fiberglass, plastics and wood where:

- Outstanding Gloss and color retention are desired.
- Outstanding adhesion and flexibility is required.
- Excellent durability and chemical resistance.
- Car finish appearance.
- Excellent DOI and leveling is required.
- Excellent performance when using air-assist airless, pressure pot, cup gun and Roller or brush application.

### Field Applications

- Light to medium industrial equipment
- Recreational boat refinishes
- Construction equipment
- Airport ground support equipment
- Truck and Trailer Refinishing
- Bus and Transit refinish
- Commercial auto and van refinish.

### Components

6H.1. K1

OG.013

OG.030

OA.014

Base

Medium Polyurethane Reducer

Slow Polyurethane Reducer

Hardener

**GlobalStar Industrial**

## GlobalStar

6H.1.K1

High Gloss

MS Acrylic Polyurethane

EU/ROW082320166H.1.K1

### Mixing Ratio

Mix:

Mix two (2) parts base color to one (1) part 0A.014 hardener.  
Reduce with Selected Reducer 15-20%

### Pot Life

2 hours @ 20° C (68° F)

### Application

Apply:

Two medium wet coats, allow 10-20 minutes flash between coats.

Spray Gun:

HVLP Gravity Feed – 1.4 – 1.6mm tip and needle  
Pressure Pot HVLP – 1.0 – 1.1mm tip and needle  
Air Assist Airless - 1.0 – 1.1mm tip and needle  
Conventional – 1.4 – 1.7mm tip and needle

Film Build:

40-50 microns – when applied as directed.

### Dry Times

Dust Free:

20 - 30 minutes @ 20° C (68° F)

Dry to Touch

6 - 7 hours @ 20° C (68° F)

Total Hardness

24 - 36 hours @ 20° C (68° F)

Force Dry

30 - 45 minutes @ 60° C (140° F)

Chemical Resistance

Maximum resistance after 7 days

### Surface Preparation

#### **Ferrous metals:**

Best Case

SA2 sandblast Blow all dust and contaminates off and apply suitable GlobalStar primer, topcoat as directed.

Second Best Case

Hot Phosphate wash system, blow dry and apply suitable GlobalStar primer, topcoat as directed.

Third Best Case

Careful mechanical abrasion. Clean all dust, oil residue, finger prints and contaminates before and after mechanical abrasion with a clean drying wax and grease removal solvent making sure all residue is removed. Apply suitable GlobalStar primer within 8 hours, topcoat as directed.

## GlobalStar Industrial



### GlobalStar

6H.1.K1

High Gloss

MS Acrylic Polyurethane

EU/ROW082320166H.1.K1

#### **Aluminum:**

Clean surface with clean drying wax and grease remover. Apply GlobalStar Epoxy Primer followed by topcoat as recommended.

#### **Galvanized Steel:**

Clean all dust, oil residue, and contaminants from surface using a Clean drying wax and grease remover. Light Sanding (320P grit) Clean again with clean drying wax and grease remover using a wipe and dry process. Apply GlobalStar Epoxy Primer followed by topcoat as directed.

#### **VOC**

Regulatory VOC National Rule

585 g/l (4.8 lbs./gl.)

Actual VOC National Rule

585 g/l (4.8 lbs./gl.)

#### **Solids**

By Volume

40%

By Weight

60%

#### **Specific Gravity**

1.12 kg/l (9.34 lbs./gl.)

#### **Coverage**

10m<sup>2</sup> / Kg (theoretical)

#### **Repainting**

After 24 hours @20° C (68° F). Light sand recommended for best adhesion. After force dry recommendations are completed, allow cool down for 1 hours before sand and recoat.

#### **Storage Stability**

One year for A (base) component, 6 months B (Hardener) Component in closed package, in cool dry place, away from any heat source.

#### **Heat Resistance**

Once cured 180° C (356° F)

### GlobalStar Industrial

**GlobalStar**

6H.1.K1

High Gloss

MS Acrylic Polyurethane

EU/ROW082320166H.1.K1

**ASTM Information:**

Test	Results	Test Methods
Abrasion Resistance	Excellent	ASTM D 4060
Adhesion	Excellent	ASTM D 4541 (1850 psi) ASTM D 3359 A/B (5/5)
Salt Spray Resistance	Excellent	ASTM B 117 (Pass 1500 hours)
Direct Impact Resistance	Very Good	ASTM D 2794 (140 in-lbs.)
Reverse Impact Resistance	Very Good	ASTM D 2794 (50 in lbs.)
Humidity Resistance	Excellent	ASTM D 2247 (Pass 1000 hours)
Film Hardness	3H	ASTM D 3363
Chemical Resistance (Rating Scale 1-10 with 10 best)	Very Good to Excellent	ASTM D 1308
	10	1% Sodium Hydrochloric Acid
	10	5% Sodium Hydrochloric Acid
	9	10% Sodium Hydrochloric Acid
	10	Ammonia
	10	Diesel Fuel
	10	1% Hydrochloric Acid
	10	1% Sulfuric Acid
	9	10% Sulfuric Acid
	10	100% Ethanol
	10	1% Phosphoric Acid
	9	10% Phosphoric Acid
	10	MEK (Methyl Ethyl Ketone)
	10	Gasoline
	9	Skydrol
	9	DOT 3 Break Fluid
QUV A	Excellent	ASTM D 4587 (1500 hours-97%)
Initial Gloss @ 60°	93 min.	ASTM D 523
Solvent Resistance	Surpassed	ASTM D 4752 (1000 MHR)
Flexibility	Excellent	ASTM D 522 Mandrel

All Technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.