

NORTHSTAR

107K0099 Acrylic Black Non-Skid

DESCRIPTION

The 107K0099 Acrylic Non-Skid is a high solids, air-dry, heavily textured coating for use in heavy traffic areas needing a non-slip surface. 107K0099 complies with various local VOC regulations. Please check your VOC requirements.

COMPONENTS

- 107K0099 Base
- H4 Hardener (optional)
- S9860/S9870/S9885/S9895 Fast/Medium/Slow/Very slow - Reducers (optional)

MIXING RATIO

107K0099 does not require hardener but will have much better durability with it. For enhanced performance, mix eight (8) parts 107K0099 color with one (1) part H4 hardener. 107K0099 is ready to apply but can be reduced for desired performance needs.

POT LIFE at 70° F

2 hours with hardener

CLEAN UP

Use **NORTHSTAR** Lacquer Thinner or zero VOC solvents. (Check local regulations)

PHYSICAL DATA

Solids wt. (as mixed without reducer)	75%
VOC as mixed	3.5
Color	Black

DRY / FLASH TIMES

Air Dry at 77° F

Flash between coats	30-60 minutes
Tape time	N/A
Dust free	60 minutes
Tack free	30 minutes
Traffic Usage	24 hours

SURFACE PREPARATION

Use **NORTHSTAR** Clean Wipe (S10) to clean substrate free of grease, dirt, and foreign contaminants.

APPLICATION

- (With no reducer) Apply one coat with brush, scraper or roller
- (With reducer added) Apply one to two coats for desired finish
- Allow 30-60 minutes between coats

SAFETY

Refer to Material Safety Data Sheet (MSDS) for complete safety instructions. The technical data sheet listed has been compiled in good faith for your convenience and guidance. No warranty, expressed or implied, is intended or given by the information on this sheet.

NORTHSTAR COATINGS

Division of Lusid Technologies, Inc. • Salt Lake City, UT • Phone 877 973-7600 • Fax 801 966-6876