



## PRIMERS & SEALERS

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GTS03362	GREENTEC 2.1 VOC SEALER	59.3567	1.5139	12.6338	35.11%	260.0817	2.1704	174.5120	1.4563
GTP210B	GREENTEC BLACK PRIMER + SEALER	52.5661	1.3070	10.9075	37.00%	289.9262	2.4195	174.2503	1.4541
GTP210W	GREENTEC WHITE PRIMER + SEALER	55.0603	1.3806	11.5216	35.00%	284.4301	2.3736	169.6590	1.4158
GTP210LG	GREENTEC LIGHT GREY PRIMER + SEALER	55.0090	1.3798	11.5152	35.00%	284.7206	2.3760	169.7643	1.4167
GTP10LG	DTM PU PRIMER	57.5456	1.4428	12.0405	31.47%	265.5988	2.2165	158.3866	1.3218
GTP10B	2K DTM PU BLACK PRIMER	50.2855	1.3268	11.0723	51.12%	239.1151	1.9955	128.4663	1.0721
GTP10W	2K DTM PU WHITE PRIMER	57.5648	1.4473	12.0786	31.71%	262.1050	2.1873	155.1656	1.2949
QP210LG	QUICKEE PRIME LIGHT GREY (GALLON)	67.4071	1.7663	14.7409	24.51%	211.4259	1.7644	142.7647	1.1914
QP210W	QUICKEE PRIME - WHITE	67.4071	1.7663	14.7409	24.51%	211.4259	1.7644	142.7647	1.1914

## CLEARCOATS

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GTC721	ULTIMATE LV CLEAR	34.1408	1.0799	9.0124	52.94%	286.1228	2.3877	139.4775	1.164
GT211	GREENTEC 2.1 CLEAR	49.8397	1.0575	8.8249	30.20%	297.18	2.48	211.0303	1.7611
GTC210	2.1 HS OVERALL CLEAR	39.8775	1.0585	8.8335	44.15%	297.1799	2.48	169.0129	1.4104
GTC625	DTM Clear	28.8481	1.0666	8.9009	60.14%	293.4296	2.4487	117.4711	0.9803
KAC21	KAC LOW VOC CLEAR	32.1568	1.0602	8.848	55.53%	288.5408	2.4079	130.4978	1.089
QC210	QUICKEE CLEAR	33.5069	1.0485	8.7497	52.03%	309.3169	2.5813	151.5616	1.2648

## ACTIVATORS & HARDENERS

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GH06	ACTIVATOR	60.3	1.225	10.2228	39.70%	0.0000	0.0000	0.0000	0.0000
GH065	FAST ACTIVATOR	50.2127	1.1743	9.8003	42.73%	137.6325	1.1486	82.9366	0.6921
GH075	MEDIUM ACTIVATOR	50.2263	1.1736	9.7937	42.56%	139.8395	1.167	84.5892	0.7059
GH085	SLOW ACTIVATOR	49.9973	1.1784	9.8346	42.90%	139.8931	1.1674	83.7119	0.6986
GH0-F	FAST LOW VOC ACTIVATOR	31.3453	1.1362	9.4819	66.54%	71.7838	0.599	23.9931	0.2002
GH0-M	MEDIUM LOW VOC ACTIVATOR	29.7954	1.1953	9.975	68.19%	71.7839	0.599	23.9929	0.2002
GH0-S	SLOW LOW VOC ACTIVATOR	28.0095	1.2715	10.611	70.10%	71.7839	0.599	23.9928	0.2002
GH045W	SUPER FAST WINTER ACTIVATOR	49.2298	1.1964	9.9846	44.19%	135.157	1.1279	78.7268	0.657
GH055W	VERY FAST WINTER ACTIVATOR	49.0912	1.1976	9.994	44.35%	135.1812	1.1281	78.5954	0.6559



## REDUCERS

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GS065	ZERO VOC FAST REDUCER	0.0000	0.7889	6.5833	100.00%	0.0000	0.0000	0.0000	0.0000
GS075	ZERO VOC MEDIUM REDUCER	0.0000	1.0638	8.8775	100.00%	0.0000	0.0000	0.0000	0.0000
GS085	ZERO VOC SLOW REDUCER	0.0000	1.3388	11.1732	100.00%	0.0000	0.0000	0.0000	0.0000
GSX075	GREENTEC LOW VOC ADHESION PROMOTER REDUCER	3.6215	1.1652	9.7241	96.08%	95.0500	0.7932	3.4863	0.0291
GT0R-F	FAST REDUCER (LV)	0.0000	0.8226	6.8653	100.00%	0.0000	0.0000	0.0000	0.0000
GT0R-M	MEDIUM REDUCER (LV)	4.0000	0.8351	6.9690	96.00%	0.0000	0.0000	0.0000	0.0000
GT0R-S	SLOW REDUCER (LV)	9.5491	0.8500	7.0939	90.45%	0.0000	0.0000	0.0000	0.0000
GT0R-VS	VERY SLOW REDUCER (LV)	12.5316	0.8711	7.2700	87.47%	0.0000	0.0000	0.0000	0.0000

## BINDERS

GB28	2.8 BASECOAT BINDER	22.4616	0.9993	8.3397	66.87%	335.2019	2.7973	106.6148	0.8897
GTB420	BASECOAT BINDER	14.0676	1.2219	10.1975	75.75%	419.1815	3.4981	124.3663	1.0379

## FACTORY PACKS

GBLACK	BLACK BASECOAT (3.5 VOC)	35.2829	1.0288	8.5858	51.44%	296.1968	2.4718	136.5896	1.1399
GWWHITE	WHITE BASECOAT (3.5 VOC)	41.2311	1.1432	9.5406	46.83%	305.8507	2.5524	136.4809	1.139
GBRIGHTWHITE	BRIGHT WHITE BASECOAT	44.3331	1.1839	9.8804	43.21%	306.4353	2.5573	147.493	1.2309