



VOC CHART

Revision 240802

CODE	NAME	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GlobalStar Toners (EZMIX)									
OH4.028	BLACK	53,2	1,03	8,60	0,00%	482,000	4,02	482,000	4,02
OH4.101	MEDIUM YELLOW	59,6	1,12	9,35	0,00%	452,000	3,77	452,000	3,77
OH4.102	LEMON YELLOW HS	57,371	1,206	10,063	0,00%	398,108	3,322	398,108	3,322
OH4.103	WARM YELLOW HS	63,325	1,153	9,623	0,00%	422,918	3,529	422,918	3,529
OH4.108	ORGANIC ORANGE	59,830	1,036	8,653	0,00%	416,047	3,472	416,047	3,472
OH4.112	LEMON YELLOW	58,742	1,062	8,865	0,00%	438,280	3,658	438,280	3,658
OH4.114	ORANGE	57,927	1,049	8,754	0,00%	441,361	3,683	441,361	3,683
OH4.119	FUCHSIA RED	42,972	0,987	8,236	0,00%	562,829	4,697	562,829	4,697
OH4.120	DEEP BLACK	64,832	1,032	8,613	0,00%	362,982	3,029	362,982	3,029
OH4.124	GREEN	57,198	1,047	8,738	0,00%	448,161	3,740	448,161	3,740
OH4.125	OCHRE YELLOW	80,963	1,667	13,915	0,00%	317,418	2,649	317,418	2,649
OH4.126	BLUE	61,328	1,040	8,680	0,00%	402,209	3,357	402,209	3,357
OH4.127	VIOLET	59,035	1,010	8,431	0,00%	413,855	3,454	413,855	3,454
OH4.129	LIGHT RED	73,609	1,118	9,328	0,00%	294,976	2,462	294,976	2,462
OH4.130	TITANIUM WHITE	91,824	1,886	15,738	0,00%	154,202	1,287	154,202	1,287
OH4.132	SCARLET RED	65,603	1,086	9,065	0,00%	373,655	3,118	373,655	3,118
OH4.133	AMARANTH VIOLET	57,691	1,037	8,650	0,00%	438,560	3,660	438,560	3,660
OH4.134	ALPHA PTHALO BLUE	58,610	1,040	8,676	0,00%	430,308	3,591	430,308	3,591
OH4.TR029	TRANSPARENT RED OXIDE	59,074	1,068	8,915	0,00%	437,198	3,648	437,198	3,648
OH4.TR030	TRANSPARENT YELLOW OXIDE	61,923	1,100	9,177	0,00%	418,711	3,494	418,711	3,494
OD7.037	MEDIUM SILVER DOLLAR ALUMINUM (HV)	44,253	1,040	8,675	0,00%	579,496	4,836	579,496	4,836
OD7.044	COARSE ALUMINUM (HV)	52,412	1,051	8,772	0,00%	500,205	4,174	500,205	4,174
GlobalBase Toners									
OH4.122	OXIDE RED	84,873	1,868	15,590	0,00%	282,587	2,358	282,587	2,358
OH4.204	LEMON YELLOW	76,150	1,642	13,700	0,00%	391,533	3,267	391,533	3,267
OD7.066	FINE ALUMINUM	44,1	1,05	8,76	0,00%	587,000	4,90	587,000	4,90
OD7.077	COARSE LENTICULAR ALUMINUM (HV)	43,617	1,039	8,672	0,00%	585,905	4,890	585,905	4,890
OD7.012	MAGNUM SILVER DOLLAR ALUMINUM (HV)	52,691	1,084	9,046	0,00%	512,834	4,280	512,834	4,280
OD7.050	EXTRA FINE ALUMINUM (HV)	48,104	1,044	8,708	0,00%	541,549	4,519	541,549	4,519
OD7.067	MEDIUM ALUMINUM	44,1	1,05	8,76	0,00%	587,000	4,90	587,000	4,90
OD7.069	BASE EXTRA COARSE ALUMINUM	42,5	1,02	8,51	0,00%	587,000	4,90	587,000	4,90
OD7.074	BASE ALUMINUM EXTRA FINE	42,5	1,02	8,51	0,00%	587,000	4,90	587,000	4,90
OD7.230	BASE MICRO WHITE	33,0	1,08	9,01	0,00%	724,000	6,04	724,000	6,04
OD7.401	BASE WHITE PEARL	45,465	1,065	8,886	0,00%	580,728	4,846	580,728	4,846
OD7.402	BASE FINE WHITE PEARL	45,465	1,078	8,993	0,00%	587,661	4,904	587,661	4,904
OD7.403	BLUE PEARL	45,465	1,078	8,994	0,00%	587,756	4,905	587,759	4,905
OD7.404	GREEN PEARL	47,470	1,081	9,021	0,00%	567,858	4,739	567,858	4,739
OD7.405	VIOLET PEARL	45,465	1,080	9,009	0,00%	588,735	4,913	588,735	4,913
OD7.406	YELLOW PEARL	45,465	1,076	8,981	0,00%	586,899	4,898	586,899	4,898
OD7.407	RED PEARL	45,465	1,081	9,022	0,00%	589,602	4,920	589,602	4,920

	CODE	NAME	% solids by weight	specific gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
Binders										
	7D.1.K1	HIGH GLOSS FAST AIR DRY ALKYD	47.007	0.981	8.186	0.00%	519.828	4.338	519.828	4.338
	L2.1.K2	LOW VOC ACRYLIC ALKYD	42.944	1.155	9.642	38.09%	326.391	2.724	219.091	1.828
	L4.1.K1	MS LOW VOC ACRYLIC POLYURETHANE	43.551	1.077	8.990	39.14%	296.054	2.470	186.475	1.556
	L4.4.K1	MS SATIN LOW VOC ACRYLIC POLYURETHANE BINDER	31.644	0.995	8.302	57.41%	290.252	2.422	108.934	0.909
	L5.1.K1	HIGH GLOSS MS ACRYLIC POLYURETHANE	48.370	0.976	8.141	0.00%	503.684	4.203	503.684	4.203
	L6.1.K1	UHS LOW VOC POLYURETHANE	41.208	1.124	9.379	44.48%	272.706	2.276	160.884	1.343
	L7.1.K1	HIGH GLOSS UHS POLYURETHANE	51.250	0.987	8.236	10.50%	447.882	3.738	404.219	3.373
	L8.3.K2	LOW VOC BASECOAT BINDER	16.552	1.173	9.787	75.71%	331.794	2.769	90.727	0.757
	L9.3.K1	BASECOAT BINDER	13.959	0.886	7.391	0.00%	762.037	6.359	762.037	6.359
	L10.1.K1	AIRLESS POLYURETHANE BINDER	71.216	1.017	8.487	0.00%	292.721	2.443	292.721	2.443
	L12.1.K1	DTM LOW VOC BINDER	47.409	1.009	8.420	26.59%	359.414	2.999	262.350	2.189
	L12.4.K1	DTM LOW VOC FLAT BINDER	51.325	1.111	9.275	26.96%	325.655	2.718	241.352	2.014
GlobalBase Binder										
	LB8	LOW VOC GLOBALBASE BINDER	16.328	1.193	9.959	76.37%	322.044	2.688	87.117	0.727
	LB9	GLOBALBASE BINDER	13.959	0.886	7.391	0.00%	762.037	6.359	762.037	6.359
GlobalBase Clear Coats and Primers										
	LC3030	GLOBALBASE NATIONAL RULE 4:1 CLEAR	32.541	0.930	7.760	15.51%	591.135	4.933	483.065	4.031
	LC3030LV	GLOBALBASE LOW VOC 4:1 CLEAR	29.092	1.106	9.234	59.78%	284.383	2.373	123.103	1.027
	LC2010LV	GLOBALBASE LOW VOC 2:1 CLEAR	39.864	1.057	8.817	43.89%	299.515	2.500	171.630	1.432
	LP3030	GLOBALBASE PRIMER	55.582	1.308	10.912	2373%	579.487	4.836	577.687	4.821
	LH60	FAST ACTIVATOR	30.047	0.948	7.915	0.00%	663.452	5.537	663.452	5.537
	LH70	MEDIUM ACTIVATOR	30.031	0.934	7.795	0.00%	653.564	5.454	653.564	5.454
	LH85	SLOW ACTIVATOR	30.019	0.962	8.032	0.00%	673.523	5.621	673.523	5.621
GlobalStar Primers										
	P6.3.K1	1K LV DTM PRIMER	58.873	1.598	13.334	31.84%	239.384	1.998	148.427	1.239
	P7.3.K1	2K ACRYLIC PRIMER FILLER	61.462	1.345	11.226	0.31%	516.404	4.309	514.258	4.292
	P8.3.K1	1K GRAY DTM PRIMER	61.148	1.307	10.909	0.00%	507.872	4.238	507.872	4.238
	P9.3.K1	HS GRAY EPOXY PRIMER	66.234	1.285	10.724	23.32%	210.738	1.759	134.250	1.120
	P10.3.K1	DTM 2K POLYURETHANE LOW VOC PRIMER	60.229	1.429	11.925	27.33%	277.047	2.312	177.786	1.484
Hardeners, Activators, Thinners & Miscellaneous										
	AE.002	HARDENER FOR 3G, 6B, L5 AND P7	50.007	0.970	8.093	0.00%	484.845	4.046	484.845	4.046
	AE.002.SLOW	SLOW ACTIVATOR	50.007	0.970	8.093	0.00%	484.845	4.046	484.845	4.046
	AH.002	HARDENER FOR L7-SERIES	81.000	1.075	8.972	0.00%	204.273	1.705	204.273	1.705
	AV.002	HARDENER FOR L2, L4, L6, AND L10	80.000	1.192	9.946	20.00%	0.000	0.000	0.000	0.000
	AV.005	HARDENER FOR LC, P12 AND L12	38.208	1.264	10.552	61.79%	0.000	0.000	0.000	0.000
	EH.001	QUICK EPOXY HARDENER FOR P9-SERIES	37.373	0.930	7.758	54.35%	197.964	1.652	76.914	0.642
	GSR-F	FAST PU REDUCER	0.000	0.847	7.070	9.00%	856.612	7.149	770.950	6.434
	GSR-M	MEDIUM PU REDUCER	0.000	0.852	7.110	0.00%	851.997	7.110	851.997	7.110
	GSR-S	SLOW PU REDUCER	0.000	0.868	7.240	0.00%	867.569	7.240	867.569	7.240
	GSOR-F	FAST ZERO VOC PU REDUCER	0.000	0.789	6.583	10.00%	0.000	0.000	0.000	0.000
	GSOR-M	MEDIUM ZERO VOC PU REDUCER	0.000	1.064	8.878	10.00%	0.000	0.000	0.000	0.000
	GSOR-S	SLOW ZERO VOC PU REDUCER	0.000	1.339	11.173	10.00%	0.000	0.000	0.000	0.000