

## PRIMERS & SEALERS

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GSEAL	G-SEAL Sealer	54.92	1.270	10.597	3.76%	558.55	4.66	524.74	4.38
GTP270	Iso Free Primer Surfacer	72.58	1.535	12.814	4.94%	381.79	3.19	345.07	2.88
GTP310	2K Urethane Primer	61.46	1.345	11.226	0.31%	516.40	4.31	514.26	4.29
GTP500	KAP500 2K Urethane Primer	61.46	1.345	11.226	0.31%	516.40	4.31	514.26	4.29

## ACTIVATORS

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GH2	Medium Activator	53.10	10.011	8.437	0.00%	474.18	3.96	474.18	3.96
GH65	Fast Activator	50.55	1.004	8.375	0.00%	496.25	4.14	496.25	4.14
GH75	Medium Activator	50.41	0.993	8.285	0.00%	492.28	4.11	492.28	4.11
GH85	Slow Activator	50.86	1.016	8.475	0.00%	499.07	4.16	499.07	4.16
GTA275	Activator	46.16	0.933	7.787	0.00%	502.37	4.19	502.37	4.19
H5070	Fast Activator	44.14	0.986	8.228	0.00%	550.78	4.60	550.78	4.60
H7085	Medium Activator	44.00	1.064	8.879	19.45%	462.79	3.86	392.50	3.28
H728	GSEAL Activator	39.85	1.080	9.014	39.62%	325.94	2.72	221.75	1.85
H8595	Slow Activator	43.97	1.112	9.280	23.27%	451.55	3.77	364.26	3.04
GH-F	Fast Activator	30.07	0.949	7.918	0.00%	663.52	5.54	663.52	5.54
GH-M	Medium Activator	30.03	0.935	7.804	0.00%	654.30	5.46	654.30	5.46
GH-S	Slow Activator	30.02	0.964	8.041	0.00%	674.30	5.63	674.30	5.63

## BASECOAT

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GBLACK	Black Basecoat (3.5 VOC)	35.28	1.029	8.586	68.23%	296.20	2.47	136.59	1.14
GWHITE	White Basecoat (3.5 VOC)	41.23	1.143	9.541	46.69%	305.85	2.55	136.48	1.14

## CLEARCOATS

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GTS40	GT Select Clear	41.82	0.944	7.875	14.67%	521.66	4.35	468.18	3.91
KAC44	KAC National Rule Clear	33.76	0.930	7.759	10.28%	592.05	4.94	520.29	4.34
GTC720	Ultimate Clear	39.16	0.942	7.861	10.45%	542.34	4.53	474.64	3.96

## FACTORY PACK

CODE	NAME	% solids by weight	Specific Gravity	lbs/gal	% total exempt	coating voc g/l	coating voc lbs/gal	material voc g/l	material voc lbs/gal
GP587	Hot Rod Satin Black	37.43	1.019	8.502	4.13%	408.41	3.41	240.68	2.01